

REINFORCING WIRE BAR



PRODUCT SPECIFICATION

Grade	» B500A
Ductility	» Normal
Surface	» Profiled, smooth and ribbed depending on national standard
Diameter	» 6 to 12 mm, in 0,5 mm (other dimensions are available on request)
Bar lengths	» On request
Fabricated	» According to standard or customer's request
Availability	» On request
Certified for following countries	» D F PL
Application	» For factory-produced reinforcements according the technical building regulations
Physical values according to DIN 488 e.g. for Germany	» Yield point R_e min. 500 MPa Ratio tensile strength / yield strength R_m/R_e min. 1,05 Elongation at max. load A_{gt} min. 2,5 % Weldable (C ≤ 0,22 %, Ceq ≤ 0,50)